

D 3.6 ProFlon White

100 % virgin PTFE, modified and filled with Barium sulfate

Characteristics

- Protected against cold flow
- Excellent recovery
- Excellent chemical resistance in caustic applications
- Reduced leakage rates compared to other filled PTFE gaskets under the same gasket stress.

Operating range

p_{max} [psi]	1090
$t^{\circ}F$	-350 ... +500
pH	0 - 14

Recommended application range vacuum
up to 580 psi, at -210 °F to +390 °F.

Main application

- Steel-, Glass-, Ceramic-, glass lined or plastic flanges on pipework
- Vessel
- Container
- Reactors

Suitable for

- Chemical and Petrochemical industry

Approvals

- TA Luft VDI 2440 and VDI 2290
- FDA



Article code / Thickness

D 3.6 WHITE 08 / 0.8 mm / 0.03"
D 3.6 WHITE 10 / 1.0 mm / 0.04"
D 3.6 WHITE 15 / 1.5 mm / 0.06"
D 3.6 WHITE 20 / 2.0 mm / 0.08"
D 3.6 WHITE 30 / 3.0 mm / 0.12"

Form of delivery

Gasket sheet size of 60" x 60"
in thickness of 0.03"/0.04"/
0.06"/0.08"/0.12" or cut gaskets
according to drawing, or EN and
international Standards, special
dimensions on request.



All technical information and advice is based on our experience and will be given most conscientiously but without any liability.


Indication and figures are for guidance only and need to be examined by the user. All sizes are subject to manufacturing tolerances. We reserve the right to modify specifications at any time.
Please note that the technical values cannot be used all at the same time in their maximum values.

ProPack AG

Rudolf-Diesel-Ring 28 . 82054 Sauerlach . Germany

Phone ++49 (0) 8104 6640 0 . Fax ++49 (0) 8104 6640 44
propack@propack.ag

www.propack.ag
TECHNOLOGY MADE IN GERMANY



Installation

Clean sealing surface completely. Remove any dirt, corrosion, grease or remainders from old sealing materials.

- Position gasket centric on the sealing surface. Take extra care on vertical assemblies. First tighten bolts finger-tight.

Then continue at least with 4 progressive torque sequences with a torque wrench, always torque crosswise as shown in the sketch (see fig. 1). Apply 25%, 50%, 75% and 100% of the recommended gasket stress.

- Always follow the state-of-the-art guidelines for gasket assembly as well as the recommended torque for your sealing system.

- Notes of the flange manufacturer and recommended torques for the sealing system (flange, bolt, gasket) need to be followed.

Gasket sheets technical data

	Compressibility ASTM F36 %	Recovery ASTM F36 %	PQR EN13555	Pressure* max* psi	Temp (Material)* max* °F	Material	Q _{min} EN13555 (MPa)	Q _{Smin} EN13555 (MPa)	Q _{Smax} EN13555 (MPa)
D 3.6 ProFlon White	12	>40	0.48 @ 30MPa: 302 °F	1,087	500	sPTFE with BaSO4	15	<10	100

*The max values of pressure and temperature cannot be used at the same time Recommended application range vacuum up to 580 psi, at -210 °F to +390 °F.

The provided Pressure and Temperature data is based on optimal installation condition and steady control of the flange connection

Gasket properties following EN 13555 (2 mm / 0.08" thickness)

Q_{min}@580 psi He, 0,01 mg/(sm)

Q_{Smin} @ QA 30MPa, 580 psi He, L=0,01

Q_{Smax} @ RT

All technical information and advice is based on our experience and will be given most conscientiously but without any liability.

Indication and figures are for guidance only and need to be examined by the user. All sizes are subject to manufacturing tolerances. We reserve the right to modify specifications at any time.

Please note that the technical values cannot be used all at the same time in their maximum values.

ProPack AG

Rudolf-Diesel-Ring 28 . 82054 Sauerlach . Germany

Phone ++49 (0) 8104 6640 0 . Fax ++49 (0) 8104 6640 44

propack@propack.ag

www.propack.ag

TECHNOLOGY MADE IN GERMANY

