



## P 60 CarboGraph

Braided from Expanded Graphite Tape with integrated Carbon fiber Reinforcement

### Characteristics

- Wear and extrusion stability through Carbon fiber reinforcement
- Non hardening, good reset capability, coefficient of thermal expansion similar to steel
- High temperature resistant and excellent heat and electric conductivity
- Self lubricating, excellent use in pumps, minimizing the need for flushwater
- Easy to cut, assemble and disassemble
- No shaft wear, excellent dry running characteristics



### Operating range

			
p [bar]	20	65	300
v [m/s]	30	3	
t °C	-200 ... +550		
pH	0 - 14		
g/cm <sup>3</sup>	1.00		

Practical useful application data:  
max. temperature in oxidizing atmosphere: +400 °C

### Main application

- Centrifugal pumps
- Valves
- Control valves
- Gate valves
- Steam
- High Pressure and Temperature Valves

### Suitable for

- Power plant technology
- Boiler houses
- Chemical industry
- Pulp and paper industry



### Form of delivery

This packing can be manufactured from 4 to 30 mm square as well as in intermediate, inch sizes and special measurements.

- 04 - 09 mm on 1 kg spool
- 10 - 15 mm on 2,5 kg spool
- 16 - 25 mm on 5 kg spool

Special length, pre-cut or die formed rings on request.

1 kg of packing of the following cross-sections is equivalent to displayed meter lengths:

Size mm	Meter	Size mm	Meter
4	62.5	12.7 [1/2"]	6.2
5 [3/16"]	40.0	14 [9/16"]	5.1
6	27.8	15	4.4
6.35 [1/4"]	24.8	16 [5/8"]	3.9
7	20.4	18	3.1
8 [5/16"]	15.6	19 [3/4"]	2.8
9.5 [3/8"]	11.1	20	2.5
10	10.0	22 [7/8"]	2.1
11 [7/16"]	8.3	25 [1"]	1.6
12	6.9		

All technical information and advice is based on our experience and will be given most conscientiously but without any liability.

Indication and figures are for guidance only and need to be examined by the user. All sizes are subject to manufacturing tolerances. We reserve the right to modify specifications at any time.

Please note that the technical values cannot be used all at the same time in their maximum values.