

Certificate

Food regulatory evaluation of PTFE stuffing box packing S6SI

Customer: ProPack Dichtungen und Packungen AG
82054 Sauerlach
Date of certificate: 21.03.2017
Order: PA/4832/16
Sample: stuffing box packing S6SI

The stuffing box packing S6SI consists of PTFE yarn and barium sulphate as a filling material. Furthermore, the packing is impregnated with the silicon oil "Silfar 1000".

The certificate is related to the investigation results of PA/4783/13 (sample 1, version without silicone oil and sample 2, version with silicone oil) and PA/4832/16 (sample 1, version without silicone oil). Within the investigations of order PA/4783/13, among other analyses dichloromethane extracts of the sample were investigated by screening test for potentially migrating volatile substances (Fraunhofer IVV test report PA/4783/13 part 3 dated 25.6.2014). For the order PA/4832/16 the screening test was repeated (Fraunhofer IVV test report PA/4832/16 dated 21.11.2016; sample 1, version without silicone oil). In addition, the sample was again tested for perfluorooctanoic acid and perfluorooctane sulfonate (Fraunhofer IVV test report PA/4832/16 part 2 dated 21.03.2017; sample 1; version without silicone oil). The chromatograms obtained by screening test showed no significant differences so that the results from order PA/4783/13 can be transferred to the present sample.

The stuffing box packing S6SI is used in food processing machinery, pipes, etc. in particular for sealing rotating shafts, etc. in armatures, pumps and stirrer units. In such applications, the stuffing box is incorporated in a housing such that there is only contact via a narrow gap with the container or pipe containing the food. Only by incident, food can come into contact with the packing when it is pressed or sprayed into the packing housing through the gap. The width of this gap is approx. 1 mm. The systems, in particular in pumps, are generally designed such that any food on the shaft entering into the packing housing is transported away from the container and does not re-enter the container. Stuffing boxes are used in processing machineries with a throughput of more than 1000 l/h.

Stuffing box packings are manufactured from impregnated, braided and pressed yarns and can therefore not be considered as typical plastic materials according to Regulation (EU) No 10/2011. However those materials are neither regulated on national nor on European level specifically. All food contact materials must comply with the requirements of Article 3 of the EU Framework Regulation (EC) No. 1935/2004. According to Article 3 (1) of this Regulation materials and articles shall be manufactured in compliance with good manufacturing practice so that, under normal or foreseeable conditions of use, they do not transfer their

constituents to food in quantities which could endanger human health; bring about an unacceptable change in the composition of the food or a deterioration in the organoleptic characteristics thereof.

The overall migration and specific migration of detected components was evaluated based on article 17 (3) and (4) of Regulation (EU) No 10/2011 for caps, gaskets, stoppers and similar sealing articles (last amendment by Regulation (EU) No 2016/1416).

In the USA, PTFE materials must comply with the requirements of 21 CFR § 177.1550 „Perfluorocarbon resins“. However, our experiences have shown that the extraction tests as given for perfluorocarbon molded articles (21 CFR § 177.1550 (1)) and perfluorocarbon intended for use as coatings or components of coatings (21 CFR § 177.1550 (2)) are not applicable for stuffing box packings. Thus the evaluation of migratable compounds was assessed according to the "Threshold of Regulation" (TOR) (21 CFR § 170.39).

The determination of barium as well as the screening test was performed on the samples without silicone impregnation. The results can be transferred to the corresponding sample with silicone oil. Migration of the silicone oil was evaluated via overall migration.

The overall migration test was performed according the European Standard EN 1186-3 and 13b with 3 % acetic acid (4 h / 100 °C) and modified polypropylene oxide (Tenax®) (2 h / 200 °C) (test report PA/4783/13, part 1 dated 31.1.2014). The specific migration limit of authorized barium containing compounds is set at 1 mg/kg food (expressed as barium). The migration of barium was performed in 3 % acetic acid (4 h / 100 °C) according to DIN EN ISO 17294-2 (test report PA/4783/13 part 2 dated 20.1.2014).

According to the data sheet provided by Wacker Chemie AG the used silicon oil "Silfar 1000" is in compliance with the specifications for polydimethylsiloxane (MG > 6800 Da) (Ref. 76721) according to Regulation (EU) No 10/2011, the BfR recommendation XV "Silicones" and 21 CFR § 173.340 "Defoaming Agents" of FDA.

For the evaluation of further potentially migratable components the dichloromethane extracts and Tenax® migrates were investigated for semi volatile organic substances by gas chromatography with FID/MS detection. Furthermore the material was analysed for fluorinated compounds by purge and trap gas chromatography with fluorine selective detection. In addition, methanol extracts were investigated specifically for perfluorocarbonic acids (PFOA), perfluorosulfonamides (PFOA) and fluorotelomer alcohols (PFOH) using LC-MS and GC-MS (test report PA/4783/13 part 3 dated 25.6.2014 and test report PA/4832/16 part 2 dated 21.03.2017).

In the extracts of the sample as well as in the Tenax® migrates polyethylene glycol alcyether-oligomers were found. These substances are covered by the substance group "polyethyleneglycol (EO = 1-50) ethers of linear and branched primary (C8-C22) alcohols" (Ref. 77708) listed in Regulation (EU) No 10/2011. Migration of the sum of these substances is restricted by a specific migration limit of 1.8 mg/kg food and 0.3 mg/dm², respectively (EU-cube: 6 dm³/kg). In USA,

this substance is approved for direct food contact without specific limitations according to 40 CFR § 180.940. Further migratable compounds, low volatile fluorinated components and FTOH were not detected at the respective detection limits.

In addition, traces of perfluoro octanoic acid (PFOA) were detected in the methanol extracts of the sample. The detected amounts do not indicate an intentional use as production aid. For this substance a TDI of 1.5 µg / kg body weight /day was set by EFSA. Taking into account a conventional assumption that 1 kg of food is consumed daily by a person of 60 kg bodyweight and that the food is packaged in a cubic container of 6 dm² surface area releasing the substance in the concentration of the migration limit this corresponds to a migration limit of 90 µg/kg food.

Based on these results the investigated stuffing box packing S6SI is in compliance with Article 3 of the Framework Regulation (EC) No 1935/2004 for the intended use as stuffing box packing (up to max. 200 °C) provided that the ratio between the contact area of the seal and the contact area of the sealed container is at least 1:1800. In addition, the sample is in compliance with the safety requirements according to 21 CFR § 170.3 (i).

Fraunhofer Institute
Process Engineering
and Packaging

Freising, 21.03.2017


Carina Gehring
(Scientist in Charge)


Petra Schmid
(Scientist)